

SIC srl Via Antonio Bruni, 2 73100 Lecce (LE) Italy

P. Iva / C.F. 04655770750 REA n° LE 308907

info@alberani.it sicsrl2014@pec.it www.alberani.it

Tel. +39 0836 936756

Banca Intesa Sanpaolo Filiale di Lecce IBAN: IT40Q0306916099100000003401 Codice BIC SWIFT: BCITITMM

DECKING BAMBOO TERMO

Technical data sheet

Product: Wood floor for outdoor spaces

Bamboo (Bambusea) **Essence:**

Processing technique: gently brushed

Finishing: Exterior natural oil

Thickness: 20 mm

Noble wood: 20 mm

Width: 140 mm

Length: 1850 mm

Installation system:

Selection: Top class (Δ) , straight and flat-cut grain and with no distinction of color, with some sound knots that bring out the natural features.

Certifications: Compliance with UNI-EN 14342:2013 on CE marking of the product and compliance with release of dangerous substances:

Pentachlorophenol content: < 5ppm

Formaldehyde emission: class E1 Thermal conductivity: 0.17 W/mk

Biological durability: class 3

Fire reaction class Dfls1



- Pentachlorophenol: < 5ppm

- Formaldehyde emissions: E1

- Thermal Conductivity: 0.17 W/mk

- Biological durability: class 3

- Density: gr/cm30,675

Fire classification: Dfls1

RECOMMENDATION

- 1) Store the product into a dry place with no temperature fluctuations. Some days before the installation the planks should be left in the room where they are about to be laid and given time to adjust.
- 2) Open the packaging carefully to avoid the damage of the planks. We recommend the disposal of packaging in accordance with current regulations.
- 3) Pay attention to sharp edges. Do not hit the planks to preserve the extreme precision of the joint system.
- 4) When laying the planks, we recommend the use of rubber-coated tools.
- 5) For a suitable installation, the screed must be dry, compact, smooth and without cracks and it may contain only 2.5% moisture at the very most. If these prerequisites are not met, do not proceed with laying the floor until proper adjustment treatments are carried out.
- 6) "Alberani Parketti" products should be preferably laid by glueing. Use only single or two-component polyurethane adhesives for glueing the planks.
- 7) Once the floor has been laid, humidity in the area has to be around 55% and the temperature kept at around 20-21°, to keep the structural features of the parquet.
- 8) Because of our strict quality control checks, our products are guaranteed if boxed: in the event of small defects, please report them promptly before the installation.